



Fiber Blend: **Kevlar®/Nomex® Blend**
 Weight: **6.5 oz/sqyd**
 Weave: **Modified Twill**
 Width: **60 Inches usable**
 Thickness: **0.014 Inch**
 Finish: **Teflon F-PPE**
 Color: **Gold / Black / Khaki**

	Initial	After Laundering	NFPA 1971 Requirements
Flame Resistance			
ASTM D 6413			
Char Length in Inch (Warp x Filling)	0.6 x 0.5	0.6 x 0.5	4.0 Max
After Flame in Second (Warp x Filling)	0 x 0	0 x 0	2.0 Max
Heat/Thermal Resistance			
NFPA 1971			
% of Shrinkage - 5mn at 500°F (Warp x Filling)	0.3 x 0.0	0.0 x 0.1	10.0 Max
Tear Resistance - Trapezoid Method			
ASTM D 5587			
Tear Strength in lbf (Warp x Filling)	84 x 87	83 x 85	22.0 Min
Cleaning Shrinkage Resistance			
AATCC 135			
% of Shrinkage (Warp x Weft)	N/A	2.7 x 0.6	5.0 Max
Spray Rating			
AATCC 22			
AATCC SCALE	100 (ISO 5)	100 (ISO 5)	90 (ISO 4) Mini
Water Absorption Resistance			
AATCC 42			
% of Absorption	0.1	0.3	30.0 Max
Breaking Strength			
ASTM D 5034			
Breaking Strength in lbf (Warp x Filling)	406 x 435	330 x 350	140.0 Min

Safety Components is registered TS 16949, ISO 9001 and ISO 14001

Information is presented in good faith and believed to be accurate. SCI makes no recommendation or representation and neither expresses nor implies a warranty as to the completeness and accuracy of data, or the use to which the information is put. Many hazards exist and users of protective materials must satisfy themselves that their usage and practices are safe.



The Technology Leader in Flame Retardant Protection

40 Emery Street
 Greenville, South Carolina 29605
 Tel: 800.896.6926 ext. 28
www.safetycomponents.com



Kevlar and Nomex are registered trademarks of E. I. du Pont de Nemours.